



Office de la propriété  
intellectuelle  
du Canada

Un organisme  
d'Industrie Canada

Canadian  
Intellectual Property  
Office

An Agency of  
Industry Canada



#4

*Bureau canadien  
des brevets*  
Certification

*Canadian Patent  
Office*  
Certification

La présente atteste que les documents  
ci-joints, dont la liste figure ci-dessous,  
sont des copies authentiques des docu-  
ments déposés au Bureau des brevets.

This is to certify that the documents  
attached hereto and identified below are  
true copies of the documents on file in  
the Patent Office.

Specification as originally filed, with Application for Patent Serial No: 2,332,189, on  
January 24, 2001, by CLAUDE BERGERON for "Plastic Recycling".

BEST AVAILABLE COPY

RECEIVED  
JAN 11 2002  
TC 1700

*S. Bregoire*  
Agent certificateur/Certifying Officer

October 19, 2001

Date

Canada

(CIPO 68)  
01-12-00

OPIC  CIPO

## PLASTIC RECYCLING

The present invention relates to recycling and more particularly, relates to the recycling of plastic materials.

The recycling in glass materials has been widely practiced for a number of years. One of the glass materials widely used for reprocessing is that of windshields in automotive and like vehicles. In the recycling process, the glass is recovered. However, windshields usually have an intermediate layer of a plastic material which normally contains a polyvinyl butyral polymer. The polyvinyl butyral polymer may be in combination with other compounds such as tetraethylen-clycol.

During the recycling of the glass material, the plastic materials are eventually removed and stock piled. Accordingly, the stock pile of material presents a potential environmental hazard.

There is, therefore, in the art a requirement for a process to recycle the plastic material and to use the recycled plastic material.

The present invention has found that one may recycle the polyvinyl butyral material by dissolving the same in a solvent and which solvent is preferably selected from one acidic acid or combinations of acetone and other materials. In particular, a combination of acetone and isopropanol has been found to be suitable.

Following the treatment of the polyvinyl butyral with the solvent to achieve a solution having a desired consistency, it may subsequently be utilized as an adhesive in various wood products.

The recycled polyvinyl butyral may be, in preferred embodiments, used in composite wood products such as plywood, presswood, and the like.

It will be understood that the above described embodiment is for purposes of illustration only and that changes or modifications may be made thereto without departing from the spirit and scope of the invention.

**BEST AVAILABLE COPY**